




## OKS 2541 - Product Information

### Fields of Application:

Protection of pipes and channels in the whole range of air-conditioning and ventilation technology. In the cladding and metal construction, e.g. at railings, bridge parts or supports.

### OKS 2541 Stainless Steel Protection, Spray



### Advantages and Benefits:

High efficiency through excellent adhesive properties and high resistance of the cured film to impact and scratches. Best use as decoration layer of all metallic surfaces. Economically due to low consumption and self-cleaning valve.

### Application:

For best use clean the surface first mechanically and then with OKS 2610/OKS 2611 Universal Cleaner. The surfaces must be metallic bright and dry. Shake can thoroughly before use. Spray an uniform thin layer on to the prepared surface from a distance of 20 - 30 cm (crosswise or with rotary movement). Local excess should be avoided. Drying and curing conditions acc. to the following technical data. For thicker layers please repeat procedure. Do not apply below +10°C and above 80% relative humidity. For additional questions please contact our technical department.

### Additional Information:

Packaging (article number):  
- 500 ml Spray (02541005)

Version:  
E-08.1/04

The data in this brochure are the result of extensive testing and experience and meet the latest stage of engineering. Due to the diversity of application possibilities and technical realities they can only be recommendations and are not arbitrarily transferable; thus no obligations, liability or warranty claims can be derived herefrom. We accept liability for the fitness of our products for particular purposes and accept such liability in writing in the individual case. In any event any justified warranty claims shall be limited to the delivery of replacement goods which are free from defect or, in the event that such subsequent improvement fails, to reimbursement of the purchase price. Any and all further claims, in particular but without limitation any liability for consequent damage, shall be excluded. Prior to use own testing must be done to prove suitability. The data are subject to change for the sake of technical progress. ® = Registered Trademark



## OKS 2541 Stainless Steel Protection, Spray

### Technical Data

	Norm	Conditions	Unit	Value
<b>Solid Lubricants</b>				
Type				stainless steel pigments
<b>Binder</b>				
Type				acrylic resins
<b>Solvents</b>				
Type				mixture
<b>Film Layer</b>				
Optimum film thickness	DIN 50 981/50 984	DIN 50 982-2	µm	20
Application Temperature			°C	20
Drying time		at 20 °C	min	60
Curing time		at 20 °C	h	48
Surface coverage			m <sup>2</sup> /tin	2 - 2,5
<b>Application Data</b>				
Density	DIN EN ISO 3838	+20°C	g/ml	0,96
Colour				bright metallic
<b>Service Temperatures</b>				
Maximum service temperature			°C	100

The data in this brochure are the result of extensive testing and experience and meet the latest stage of engineering. Due to the diversity of application possibilities and technical realities they can only be recommendations and are not arbitrarily transferable; thus no obligations, liability or warranty claims can be derived herefrom. We accept liability for the fitness of our products for particular purposes and accept such liability in writing in the individual case. In any event any justified warranty claims shall be limited to the delivery of replacement goods which are free from defect or, in the event that such subsequent improvement fails, to reimbursement of the purchase price. Any and all further claims, in particular but without limitation any liability for consequent damage, shall be excluded. Prior to use own testing must be done to prove suitability. The data are subject to change for the sake of technical progress. ® = Registered Trademark